



# GLENDORE SAND & STONE (PTY) LTD

P.O. Box 5780  
Walmer  
6065

Erf 722  
Sardinia Bay Road  
Lovemore Park  
Port Elizabeth  
6070

Tel: 041 366 1917  
Fax: 041 366 1193  
info@glendoresand.co.za  
www.glendoresand.co.za

Registration number 2006/007189/07

Director: DO Eales

## PRODUCT SPECIFICATIONS - COEGA KOP QUARRY

**MATERIAL :** 53.0mm Sub-base(crushed mat: G5)

**SOURCE :** COEGA QUARRY

**TYPE :** CRUSHED QUARTZITIC SAND STONE

### TECHNICAL DATA

<u>GRADING AIM</u>			<u>PROPERTIES</u>	
<u>SIEVE (MM)</u>	<u>% PASS</u>	<u>ACT. AVE</u>		
53.0	.....	100	Flakiness Index	: N/A
37.5	.....	100	A.C.V.	: 19.1
26.5	.....	99	Loose Bulk Density	: 1.598
19.0	.....	99	C.B.R. at 100%	: 116
13.2	.....	90	at 98%	: 91
4.75	.....	67	at 95%	: 63
2.00	20 - 70	42	Ave: Modd. AASHTO	: 2173
0.425	.....	21	Ave: O.M.C.	: 5.8
0.075	.....	13	Plastic Index	: SP
			Grading Modulus	: 2.25

**REMARKS:** As per COLTO spec.- Table 3402/1.  
Above as a guide only.  
.....  
S.Moosa.  
.....  
(Technical Controller).  
.....

Joint venture with

